

mediaJET® PMC 260FD „bright white“ | Silk matt photo paper FastDry

Product description

Absolutely brilliant white photo paper with a silk-gloss, microporous ink receiving layer. Developed for optimum high-contrast image quality in black-and-white photography. The great velvety feel, combined with the achievement of maximum colour space in the image reproduction, make a unique impression. The ideal, bright white supplement to PMC 260FD premium.

Specific feature

Universally applicable weighty photo-satin paper with a satin-glossy bright white surface which shows a practically immediate smearless drying and excellent water resistance. Colour images are reproduced in an almost photo-realistic way, true colors, living and rich in detail. mediaJET PMC 260FD bright white is a high-quality photo paper for the universal use on all common LFP inkjet plotters using dye-based as well as pigmented inks. The coating of this genuine photo basic paper shows an excellent colour reproduction at high truth of detail, sharpness of outline, an extreme great color complexity and excellent flatness. mediaJET PMC 260 FD bright white is an inkjet paper for highest requirements. The satin mediaJET PMC 260FD bright white with high resolution can be laminated cold. Due to its robust surface in many cases lamination is not necessary when used in the indoor area.

Processing

To guarantee optimal quality, photo and fine art papers should be stored and processed in a climate with 30-70% relative humidity and at temperatures from 15-30°C. We recommend that the paper be acclimatised in the print room for one day before printing, and to reseal in the original package after printing. Prevent fingerprints on the coated side by wearing clean cotton gloves while processing. Please avoid contact with solvent, glue and softener, leads to yellowing.

Technical specification

Material:	Paper	Colour L:	96,9
Application Area:	only indoor	Colour a:	1,1
Surface:	silk matt	Colour b:	-9,95
Specific gravity:	260,00g/m ²	Specular gloss:	50 ± 5 %
Thickness:	265,00µm	Opacity:	96 %
B1-cert.:	no	Rigidity md (ISO 2493):	2,4 mN
water resistant:	no	Rigidity cd (ISO 2493):	1,3 mN
Cold lamination:	yes	Display Performance Rating	light resistance D.P.R.
Heat lamination:	yes	89 years, at	light intensity 500 [lx] x 10h
Whiteness (R457):	97 ± 2 %	Optical density, start of test	D= 1.0
Smoothness (Bekk)	>750S	Test printer Epson	Stylus Photo R2400 (pig. K3)

This information consists of standard values for your guidance. Before using our print media, please check their suitability to your printer and for your intended application. Taking account of technical development, product specifications may be amended without prior notice at any time. There is no guarantee that the same results can be achieved. We not accept liability for any errors resulting from technical changes in printers and / or inks.